

CT 44

Acrylic paint



To paint buildings' façades and interiors

CHARACTERISTICS

- ▶ limits the process of concrete carbonisation
- ▶ crack bridging
- ▶ low absorbability and high elasticity
- ▶ resistant to weather conditions
- ▶ damage resistant
- ▶ BioProtect formula – resistant to the development of fungus, algae and mould
- ▶ available in full palette of Ceresit Colours of Nature®

SCOPE OF USE

Ceresit CT 44 is used for protecting façades, concrete constructions, interiors. It can be applied on the mineral substrates (concrete, cement plasters, lime-cement plasters and lime plasters). This paint can be used for painting Ceresit: CT 34, CT 35 and CT 137 mineral plasters, Ceresit: CT 60, CT 63, CT 64 acrylic plasters applied on traditional substrates and within Ceresit ETICS (External Thermal Insulation Composite Systems) with the application of EPS-boards (Expanded Polystyrene boards). This paint is a part of the concrete repair and concrete protection system Ceresit PCC. The structure of the coating ensures a high degree of protecting against CO₂ diffusion, which considerably reduces the process of concrete carbonisation. The façades covered with the paint CT 44 can be washed with washing devices operating under low pressure. The exposure of the façade to the sun causes dangerous tensions, therefore dark colours should be used only on small areas, e.g. architectural details. The paint CT 44 is protected from biological paralyses, e.g. fungus, mould, and algae.

SURFACE PREPARATION

The paint CT 44 may be applied on carrying, smooth, dry and clean substrates (free from any substances that decrease adhesion such as grease, bitumen, dust):

- concrete (age over 28 days)
- traditional cement plasters, lime-cement plasters and lime plasters (age over 14 days),



- thin-layer mineral and mineral-polymer plasters (age over 7 days),
 - thin-layer acrylic plasters (age over 3 days),
 - gypsum substrates (only inside the buildings) with the humidity below 1%, firstly primed with Ceresit CT 17,
 - gypsum cardboards, gypsum-fibre boards (only inside the buildings), fixed according to the recommendations of the board manufacturers, firstly primed with CT 17,
 - strong paint coats with good adhesion to the substrate.
- Firstly uneven and damaged substrates should be repaired. Plaster filler Ceresit CT 29 can be used for repairs. It is recommended to check the strength of the existing mineral layers. The existing dirt, layers of low strength, lime and adhesive paint coatings as well as the remainders of wall paper or glues should be completely removed. It is recommended to use washing devices. After being washed with water, the substrate should dry.

APPLICATION

Before the paint application, the content of the container should be carefully stirred by means of the drill with a mixer for about 2 minutes. Usually it is sufficient to paint twice. Between the application of the subsequent layers the 4- to 6-hour technological breaks should be maintained. CT 44 should be applied by means of a brush, roller or a sprinkling device. It is important to apply the paint evenly. If there is such a need, it is possible to add not more than 10% of water and stir carefully. Neither rusty containers nor tools should be used. Work on one surface should be carried on without any breaks using the paint of the same badge number printed on each packaging or the content of containers with different badge numbers should be mixed together. The area not to be painted, e.g. windows, doors should be protected (e.g. with foil). Bushes, other plants, etc. should be protected as well. Any stains should be immediately rinsed with water. Tools should be washed carefully with water directly after being used.

PLEASE NOTE

Application should be performed in dry conditions with the ambient and substrate temperature ranging from +5°C to +25°C and the humidity below 80%.

All the data refer to the temperature of +20°C and relative humidity of 60%. Faster or slower drying of this product may occur in different conditions. The paint may cause decolouration impossible to be removed on glass, ceramic, wooden, metal and stone surfaces, therefore all the elements in contact with CT 44 should be protected. Skin and eyes should be protected. Protective gloves and glasses should be worn while applying the paint. Stains should be carefully rinsed with water. In case of contact with eyes, they should be rinsed with water and the general practitioner should be consulted. This product should be stored out of reach of children.

OTHER INFORMATION

This paint should not be applied on strongly sunny surfaces. This product should not be mixed with other paints, pigments or binders. The façade should be protected against rain until the paint dries completely. It is recommended to use scaffolding protection. The opened container should be carefully closed and its content should be used as soon as possible.

This technical data sheet determines the scope of application of the material and the way of conducting the work, however, it cannot replace the professional preparation of the contractor. Apart from the data provided, the application should be done in compliance with the construction and industrial safety regulations.

The manufacturer guarantees the quality of the product, however, he does not have any influence on the condition and the way of application. In case of any doubts, individual application trials should be conducted. The previously issued technical data sheets become invalid with the issue of this Technical Data Sheet.

STORAGE

Up to 12 months since the production date when stored in cool conditions and in original undamaged packages.

Protect against frost!



Henkel CEE GmbH
Erdbergstr. 29
A-1030 Vienna, Austria
www.henkel-cee.com

PACKAGING

Plastic containers of 15 l.

TECHNICAL DATA

Base: dispersion of acrylic resins with mineral fillers and pigments

Density: approx. 1.4 kg/dm³

Temperature of application: from +5°C to +25°C

Resistance to rain: after approx. 12 h

Assumed consumption: depending on the smoothness and absorption of the substrate, on average approx. 0.3 l/m² with two coatings

Resistance to scrubbing acc. PN-C-81913: > 15000 cycles the layer

Water permeability acc. EN 1062-1: W3

CO₂ permeability acc. EN 1062-1: C1

Shine acc. EN 1062-1: G3

Grain size acc. EN 1062-1: S1

Assess the degree of blistering acc. EN 1062-1: lack

Evaluation of the cracks acc. EN 1062-1: cat. 0, lack

Assessment of the degree of exfoliation acc. EN 1062-1: cat. 0, lack

Fire classification:
B – s1, d0 in: Ceresit Ceretherm Popular
Ceresit Ceretherm Classic

pH: approx. 9

This product possesses:

- European Technical Approval (ETA) in systems:

Ceresit Ceretherm System	Popular	Popular (E)	Classic	Classic (R)	Classic (B)	Classic (S)	Classic (E)	Premium	Premium (B)
ETA	08/0309	10/0229	09/0014	09/0095	09/0097	09/0096	10/0228	08/0308	09/0137
Certificate	1488-CPD-0102/W	1488-CPD-0199/W	1488-CPD-0104/W	1488-CPD-0108/W	1488-CPD-0107/W	1488-CPD-0110/W	1488-CPD-0200/W	1488-CPD-0103/W	1488-CPD-0109/W
DoC:	WE-CC	WE-CC	WE-CC	WE-CC	WE-CC	WE-CC	WE-CC	WE-CC	WE-CC
Ceresit Ceretherm	Popular 2/PL	Popular 2/EE	Classic 2/PL	Classic 2/RO	Classic 2/BG	Classic 2/RS	Classic 2/EE	Premium 2/PL	Premium 2/BG
	15.02.2012	15.02.2012	15.02.2012	15.02.2012	15.02.2012	15.02.2012	15.02.2012	15.02.2012	15.02.2012

- Technical Approvals in Systems:

Ceresit Ceretherm System	Popular	Classic	Premium	Express	Reno
TA	15-6894 /2008 + Annex No. 2	15-4397 /2008 + Annex No. 2	15-6986 /2008 + Annex No. 2	15-7152 /2010 + Annex No. 1	15-8077 /2009 + Annex No. 1 and 2
Certificate	ITB-0068/Z	ITB-0109/Z	ITB-0108/Z	ITB-0173/Z	ITB-0355/Z
DoC:	Popular	Classic	Express	Express	Reno
Ceresit Ceretherm	/2/12/	/2/12/	Premium /2/12/	/3/12/	/3/12/
	15.02.2012	15.02.2012	15.02.2012	15.02.2012	15.02.2012